



SCHEDA TECNICA PRODOTTO

Technical Product Information

Prodotto / Product Spunbonded Polypropylene

Tipo / Style Filter SMS 30/35/15

idrorepellente Codice Prodotto / Product Code Securon 80

Dati Tecnici / Technical Data

Proprietà / Property	Unità di misura Unit		Specification Target	Tolerance	Test Method
Peso / Basis Weight	g/m ²		80	+/- 10%	WSP 130.1
Spessore / Thickness	mm		0,25	+/- 10%	WSP 120.6 (05)
Resistenza a rottura Tensile Strength	kN/m	LD/MD	110	+/- 10%	WSP 110.4
		TD/CD	50		
Allungamento Elongation at break	%	LD/MD	50	+/- 10%	WSP 110.4
		TD/CD	70		
Air permeability	l/m ² *s		200		WSP 70.1

This is not a specification. Properties are given as typical values. As the conditions of use are beyond our control, we disclaim any liability, including for patent infringement, incurred in connection with the use of these products, data or suggestions, wether used alone or in combination with other materials.

Quality departement, 2016

AMETERA SRL

Via G.Galileo, 3/C1 I-31011 Asolo (TV) Italy
Tel. +39 0423 951322 Fax +39 0423 951322 e-mail: ametera@ametera.it

26/03/2020



SCHEDA TECNICA PRODOTTO

Technical Product Information

Prodotto /Product Spunbonded Polypropylene
Tipo / Style Filter SMS 30/35/15
idrorepellente Codice Prodotto / Product Code Securon 80 E

Dati Tecnici / Technical Data

Proprietà / Property	Unità di misura Unit		Specification Target	Tolerance	Test Method
Peso / Basis Weight	g/m ²		80	+/- 10%	WSP 130.1
Spessore / Thickness	mm		0,25	+/- 10%	WSP 120.6 (05)
Resistenza a rottura Tensile Strength	kN/m	LD/MD	98	+/- 10%	WSP 110.4
		TD/CD	50		
Allungamento Elongation at break	%	LD/MD	60	+/- 10%	WSP 110.4
		TD/CD	75		
Air permeability	l/m ² *s		200		WSP 70.1

This is not a specification. Properties are given as typical values. As the conditions of use are beyond our control, we disclaim any liability, including for patent infringement, incurred in connection with the use of these products, data or suggestions, wether used alone or in combination with other materials.

Quality departement, 2016

AMETERA SRL

Via G.Galileo, 3/C1 I-31011 Asolo (TV) Italy
Tel. +39 0423 951322 Fax +39 0423 951322 e-mail: ametera@ametera.it

26/03/2020



SCHEMA TECNICA PRODOTTO

Technical Product Information

Prodotto / Product Spunbonded Polypropylene

Tipo / Style 100% Polypropylene (PP)

idrorepellente

Codice Prodotto / Product Code SPUNTEN 40 HO

Dati Tecnici / Technical Data

Proprietà / Property	Unità di misura / Unit		Specificati on Target	Tolerance	Test Method
Peso / Basis Weight	g/m ²		40	+/- 8%	WSP 130.1 (09)
Spessore / Thickness	mm		0,31	+/- 10%	WSP 120.6 (05)
Resistenza a rottura / Tensile Strength	N/5cm	LD/MD	85	+/- 10%	WSP 110.4 (09)
		TD/CD	70		
Allungamento / Elongation at break	%	LD/MD	73	+/- 10%	WSP 110.4 (09)
		TD/CD	77		
Air Permeability	l/m ² /s		1550		WSP 70.3

This is not a specification. Properties are given as typical values. As the conditions of use are beyond our control, we disclaim any liability, including for patent infringement, incurred in connection with the use of these products, data or suggestions, wether used alone or in combination with other materials.

Quality departement, 03.06.2019

Ametera srl

Via G.Galilei,3/C1 I-31011 Asolo

(TV) Italy

Tel. +39 0423 951322

Fax +39 0423 951322

e-mail: ametera@ametera.it